

ege group testcertificate

Herning d. 2020-01-30

Subject:	Classification
Reference No.:	1281
Reference:	Contra wt
Dimension:	Roll
Description of sample:	Tuftet loop pile 100 % Polyamide Woven textile
Testing atmosphere	Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles EN ISO 139:2005 of 65 ± 4 % R.H. and 20 ± 2 °C.

Testmethod	Testresults	Requirements
Total mass (g/m ²) ISO 8543	2200	
Total thickness (mm) ISO 1765	5,2	
Thickness of pile above substrate (mm) ISO 1766	2,9	
Mass of pile above substrate per unit area (g/m ²)	391	
Surface pile density (g/cm ³) ISO 8543	0,170	
Number of tufts or loops (per m ²)	164.804	
Vettermann/Hexapod ISO 10361 Short turn Long turn	Note 4-5 Note 4	
Castor chair suitability EN 985 Test A 5.000T 25.000T	Note 4 Note 3 r = 3,8	Intensive use r ≥ 2,4
Fibre bind <80% natural fibres EN 1963 C 400T	Pass	Better than photographs
Suitable for use on stairs EN 1963 B 2.000T	Pass	
Body voltage ISO 6356	1,5 kV	≤ 2 kV
Resistance to fraying EN 1814	Pass	
Basic requirements	Fulfilled	
Use Class	33 Class	

The information contained on page no 1-1 of this certificate is hereby certified to be correct statement of the tests and investigations carried out by ege testlaboratory on the material referred to.

Signed by

Reported By

Lene M. Weissenborn

Lene M. Weissenborn
Laboratory Technician



Henrik Schmidt Hansen
GROUP CSR DIRECTOR