

**ege testcertificate**

Herning 2024-04-19

<b>Subject:</b>	Classification
<b>Reference No.:</b>	B-3296
<b>Reference:</b>	Ambassador CF
<b>Dimension:</b>	Rug
<b>Description of sample:</b>	Tuftet loop pile 100 % wool Floor covering with pile Felt Backing
<b>Testing atmosphere</b>	Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles EN ISO 139:2005 of 65 ± 4 % R.H. and 20 ± 2 °C.

Testmethod	Testresults	Requirements
<b>Total mass (g/m<sup>2</sup>)</b> ISO 8543	3729	
<b>Total thickness (mm)</b> ISO 1765	13,14	
<b>Thickness of pile above substrate (mm)</b> ISO 1766	7,3	
<b>Mass of pile above substrate per unit area (g/m<sup>2</sup>)</b>	1104	
<b>Surface pile density (g/cm<sup>3</sup>)</b> ISO 8543	0,152	
<b>Number of tufts or loops (per dm<sup>2</sup>)</b>	30.222	
<b>Vettermann</b> ISO 10361 Short turn Long turn	Note 2-3 Note 2	
<b>Fiber bind</b> ≥80% natural fibres ISO/PAS 11856 at 30.000 rubs 10.000 rubs 10.000-30.000 rubs	25 mg 0,0029 mg pr rub	<250 mg <0,0035 g per rub
<b>Basic requirements</b>	Fulfilled	
<b>Use Class</b>	Class 22	

The information contained on page no 1-2 of this certificate is hereby certified to be correct statement of the tests and investigations carried out by ege testlaboratory on the material referred to.

Signed By



Lene M Weissenborn  
Laboratory Technician

Reported By



Villads Chester  
Global Quality Manager