



TEST REPORT

DATE: 11-20-2017

TEST NUMBER: 0242235

CLIENT	Egetaepper a/s
---------------	----------------

TEST METHOD CONDUCTED	AATCC 165 Colorfastness to Crocking - Textile Floor Coverings (AATCC Crockmeter Method)
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Epoca Silky ECT350
COLOR	Navy
LOT NUMBER	134211
CONSTRUCTION	Cut Pile
BACKING	Attached Cushion

GENERAL PRINCIPLE

This method is designed to determine the degree of color which may be transferred from the surface of colored textile material to other surfaces by rubbing. Color transferred to the white test cloth is assessed by comparison with the AATCC Chromatic Transference Scale.

TEST RESULTS

COLOR/IDENTIFICATION	Wet Crock Rating	Dry Crock Rating
Navy / Epoca Silky ECT350	5.0	5.0

COLOR/IDENTIFICATION	Wet Crock Rating	Dry Crock Rating

AATCC RATING KEY	
5	No change
4	Slight change
3	Noticeable change
2	Considerable change
1	Severe change

APPROVED BY:



714 Glenwood Place

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab. Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.

Dalton, GA 30721

706-226-3283

Fax: 706-226-6787



protest@optilink.us