

## **TEST REPORT**

**CLIENT** Egetaepper a/s

TEST METHOD CONDUCTED AATCC 16 Colorfastness to Light (Option 3)



DESCRIPTION OF TEST SAMPLE			
IDENTIFICATION	Epoca Silky wt		
CONSTRUCTION	Cut Pile		
BACKING	Woven Synthetic		

## **GENERAL PRINCIPLE**

This test specimen is exposed to a predetermined amount of radiant energy under specified conditions of temperature and relative humidity. The lightfastness of the specimen is assessed by comparing the exposed and the unexposed portions of the test sample with the AATCC Gray Scale for Evaluating Color Change.

## **TEST RESULTS**

EXPOSURE	40 AFU
----------	--------

COLOR	RATING	IDENTIFICATION	RATING
Epoca Silky wt	5.0		

IDENTIFICATION	RATING

AATCC RATING KEY				
5	No change			
4	Slight change			
3	Noticeable change			
2	Considerable change			
1	Severe change			

APPROVED BY:

Day aslury



