

TEST REPORT

CLIENT Egetaepper a/s

Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF 1-70) also referenced as ASTM
D2859



DESCRIPTION OF TEST SAMPLE					
IDENTIFICATION	Epoca Silky wt				
CONSTRUCTION	Cut Pile				
BACKING	Woven Synthetic				

GENERAL PRINCIPLE

This test method is intended to measure the response of finished textile floor covering materials when exposed to an ignition source under controlled laboratory conditions. It is applicable to all types of textile floor coverings whether constructed from natural or man-made materials.

TEST CRITERION

The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.

TEST RESULTS

	SPECIMEN NUMBER									
	1	2	3	4	5	6	7	8		
Uncharred Area (Inches)	3.5	3.4	3.5	3.5	3.6	3.5	3.4	3.5		

NOTE: This sample was tested on the face side.

This sample PASSES the Federal Flammability Standard DOC FF 1-70.

APPROVED BY:

Day asluy





