

ege testcertificate

Herning 2024-04-19

Subject:	Classification
Reference No.:	B-3296
Reference:	Noble CF
Dimension:	Rug
Description of sample:	Tufted cut pile 100 % wool Floor covering with pile Felt Backing
Testing atmosphere	Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles EN ISO 139:2005 of 65 ± 4 % R.H. and 20 ± 2 °C.

Testmethod	Testresults	Requirements
Total mass (g/m²) ISO 8543	3007	
Total thickness (mm) ISO 1765	12,99	
Thickness of pile above substrate (mm) ISO 1766	9,9	
Mass of pile above substrate per unit area (g/m²)	1467	
Surface pile density (g/cm³) ISO 8543	0,148	
Number of tufts or loops (per dm²)	46.256	
Vettermann ISO 10361 Short turn Long turn	Note 2-3 Note 1-2	
Body voltage ISO 6356	0,6 kV	≤ 2 kV
Basic requirements	Fulfilled	
Use Class	Class 21	

The information contained on page no 1-2 of this certificate is hereby certified to be correct statement of the tests and investigations carried out by ege testlaboratory on the material referred to.

Signed By



Lene M Weissenborn
Laboratory Technician

Reported By



Villads Chester
Global Quality Manager